



EP64™ Bearing Material	Characteristics	Applications
	<ul style="list-style-type: none"> <li>• Injection moulded reinforced polyetheretherketone based and modified bearing material</li> <li>• High temperature material with low thermal expansion for demanding components</li> <li>• Good chemical and hydrolysis resistance</li> <li>• Excellent in lubricated applications</li> <li>• High viscosity and mechanical strength</li> <li>• High wear resistance in oscillating movements</li> <li>• Colour: black</li> </ul>	<p><b>General</b> Generally applicable within the limits of the material properties</p> <p><b>Industrial</b> Domestic appliances, transportation equipment, apparatus engineering, conveyor equipment and many more</p>

Composition & Structure	Operating Conditions	Availability										
<p>Injection moulded thermoplastic dry bearing material PEEK + PTFE + Graphite + Carbon fibres</p>	<table border="1"> <tr> <td>dry</td> <td>fair</td> </tr> <tr> <td>oiled</td> <td>good</td> </tr> <tr> <td>greased</td> <td>good</td> </tr> <tr> <td>water</td> <td>fair</td> </tr> <tr> <td>process fluid</td> <td>good after resistance testing</td> </tr> </table>	dry	fair	oiled	good	greased	good	water	fair	process fluid	good after resistance testing	<p><b>Ex Stock</b></p> <ul style="list-style-type: none"> <li>• N/A</li> </ul> <p><b>To order</b></p> <ul style="list-style-type: none"> <li>• Bushes, special dimensions and shapes</li> </ul>
dry	fair											
oiled	good											
greased	good											
water	fair											
process fluid	good after resistance testing											

Microsection	Bearing Properties	Unit	Value
 <p>Injection moulded thermoplastic dry bearing material with additives homogeneously mixed in</p>	<p><b>Dry</b></p> <p>Maximum sliding speed v</p> <p>Maximum pv factor The pv Limit is depending on the heat dissipating surface to contact area ratio 1) <math>A_H/A_C = 5</math>    2) <math>A_H/A_C = 10</math>    3) <math>A_H/A_C = 20</math></p> <p>Coefficient of friction f</p> <p><b>Grease lubrication</b></p> <p>Maximum sliding speed v</p> <p>Maximum pv factor</p> <p>Coefficient of friction f</p> <p><b>General</b></p> <p>Maximum temperature <math>T_{max}</math></p> <p>Minimum temperature <math>T_{min}</math></p> <p>Maximum load p static</p> <p>Shaft surface finish <math>R_a</math></p> <p>Shaft hardness</p>	<p>m/s</p> <p>MPa x m/s</p> <p>–</p> <p>m/s</p> <p>MPa x m/s</p> <p>–</p> <p>°C</p> <p>°C</p> <p>MPa</p> <p>µm</p> <p>HV</p>	<p>1.0</p> <p>1) 0.09 2) 0.35 3) 1.40</p> <p>0.3 - 0.5</p> <p>-</p> <p>-</p> <p>-</p> <p>+290</p> <p>-100</p> <p>125</p> <p>0.3±0.2</p> <p>&gt;450</p>